



Product Data Sheet 1FLAKE

General Product Description

	Min	Max	Target
%Carbon (LOI)	90	100	<input type="checkbox"/>
%+50 Total (300 Micron)	35	100	<input type="checkbox"/>
%+80 Total (180 Micron)	85	100	<input type="checkbox"/>

Type: FLAKE

Typical Analysis

(U.S. Standard Test Sieves)

%Carbon (LOI)	91.67
%+30 Mesh (600 Micron)	1.04
%+40 Mesh (425 Micron)	14.66
%+50 Mesh (300 Micron)	42.15
%+60 Mesh (250 Micron)	23.55
%+80 Mesh (180 Micron)	13.92
%-80 Mesh (180 Micron)	4.96

Test Methods

%Carbon	E4-1
Sieve Analysis	E2-1

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: REVISION 2

Revision Date:

12/18/2001

Asbury Graphite Mills, Inc.

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

Tel: (908) 537-2155 **Fax:** (908) 537-2108 **http://** www.asbury.com